



### Special cleaning processes: removal of antireflection and hard coatings

Bath	Product	Concentration	Temperature	Time
1	<b>deconex OP 141</b>	30-50%	40-60 °C	30 - >60 min depending from coating system
2	Rinse tap water	-	room temperature	3-5 min
3	Rinse DI water	-	room temperature	3-5 min
4	Rinse DI water	-	room temperature - 50 °C	3-5 min
5	Drying	-	70 °C	3-5 min