

# deconex<sup>®</sup> de-coat 510

**For the removal of hard lacquer  
coatings on organic materials**

Suitable for use in ultrasound baths



## Usage

deconex<sup>®</sup> de-coat 510 is a liquid product that is used for the removal of:

- hard lacquer coatings
- anti-reflective coatings (partly)

on the following substrates:

- organic lenses

Before decoating can take place, certain technical requirements must first be met. We recommend that you contact us in this regard.

## Ingredients

Alkali, chelating agent, surfactants

## Application

The following application conditions have been found to be effective in practice:

Coating	Dosage	Temperature	* Decoating time
Hard lacquer coatings	100%	60-65°C	Dependent on the coating
Anti-reflective coatings	100%	70-75°C	Dependent on the coating

\* The decoating time depends on the coating quality, coating structure and coating thickness.

Important additional informations on the application can be found in the decoating instruction.

# deconex® de-coat 510

## Instructions for use

The substrates must be cleaned oil-free and grease-free before decoating; Borer Chemie AG offers suitable cleaning solutions for this.

For the implementation of the decoating please use our decoating instructions.

## Neutralisation/disposal

Please refer to our disposal instructions for information on disposal.

It should be noted: The used decoating solution must be disposed of professionally by a disposal company. The safety data sheet can be referred to for this purpose. Locally applicable waste water and disposal regulations must be complied with.

## Chemical-physical data

pH value	1% solution in demineralised water	approx. 12.5
Density	Concentrate	1.15 g/mL
Appearance	Concentrate	clear, colourless

## Delivery

Please ask your representative regarding current container sizes.

Containers, screw caps, seals and labels are made from recyclable polyethylene.

## Material compatibility

Suitable for:  
Organic materials

Not suitable for:  
Types of fine optical glass that are sensitive to alkaline chemicals.

Independent compatibility tests should be carried out on materials other than those specified or requested from Borer Chemie AG.

## Additional information

Information regarding safety in the workplace, storage, disposal and waste water treatment can be found on the safety data sheet for this product and in the decoating and disposal instructions.

For professional use only.

For more information about the product and its use, please contact your supplier or Borer Chemie AG.

Benefit from our expertise! Ask us for practical information about your specific application.

### Manufacturer:

#### Borer Chemie AG

Gewerbestrasse 13, 4528 Zuchwil / Switzerland  
Tel +41 32 686 56 00 Fax +41 32 686 56 90  
office@borer.ch, www.borer.ch

All information provided is based on our knowledge as it currently stands, however it does not constitute any guarantee of product properties and does not form the basis of any legal relationship.